

Technical Characteristics:

Basis	MS Polymer
Consistency	Stable Paste
Curing	Moisture Curing
Skin Formation (*) (20°C/65% R.V.)	Ca. 5 min.
Curing Speed (*) (20°C/65% R.V.)	3 mm/24h
Hardness	64 ± 5 Shore A
Density	1,47 g/ml
Elastic Recovery (ISO 7389)	> 75%
Maximum Allowed Distortion	± 20%
Temperature Resistance	-40°C → 90°C
Max. Tension (DIN 53504)	3,50 N/mm²
Elasticity Modulus 100% (DIN 53504)	2,30 Nmm²
Elongation at Break (DIN 53504)	400%
Application Temperature	-5°C → 35°C

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates

Product:

Sumogrip white is a high quality, neutral, elastic, one-component adhesive sealant based on MS-Polymer with a very high initial tack. Sumogrip white is a KOMO-certified construction adhesive based on BRL3107.

Applications:

- Sealing and bonding in the building and construction industry.
- Elastic bonding of panels, profiles and other pieces on the most common substrates (wood, MDF, chipboard, etc).
- Elastic structural bonding in car and container industry.

Properties:

- High initial tack reducing the need for initial support.
- Fast curing
- Good extrudability
- High shear strength after full cure (no primer)
- Stays elastic after curing and very sustainable
- No odour.
- Can be painted with water based systems
- Good colour stability, weather and UV resistance
- Does not contain isocyanates and no silicones
- Good adhesion on wet substrates

Shelf life:

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Chemical Resistance:

Good resistance to water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis and (salt) water. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Packaging:

- Colour: White
- Packaging: Cartridge 290ml

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. DIPT Group reserves the right to modify products without prior notice.

Substrates:

- *Substrates:* all usual building substrates, treated wood, PVC, plastics.
- *Nature:* clean, dry, free of dust and grease.
- *Surface Preparation:* Porous surfaces should be primed. All smooth non-porous surfaces can be treated with a contact cleaner and thinner solution.
- We recommend a preliminary adhesion test on every surface.

Joint Dimensions:

- Minimal width: 2mm (bonding)
5mm (joints)
- Maximal width: 10mm (bonding)
30mm (joints)
- Minimum depth: 5mm (joints)
- Recommendation (sealing jobs): width of joint = 2 x depth of joint

Application:

- *Application Method:* With a manual, electric or pneumatic caulking gun.
- *Cleaning:* immediately after use.
- *Finishing:* with a soapy solution before skinning.
- *Repair:* with the same material.

Health and Safety Recommendation:

- Take the usual labour hygiene into account.
- Consult label for more information.

Standards:

- NL: KOMO certificate Nr. 33275 construction adhesive based on BRL3107.

Remarks:

- Sumogrip white may be overpainted with water based paints, however due to the large number of paints and varnishes available, we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.
- Sumogrip white can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate etc. may differ from manufacturer to manufacturer, we recommend preliminary compatibility test.
- While producing plastics, very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding.
- Sumogrip white cannot be used as a glazing sealant.
- Sumogrip white can be used for bonding of natural stone, but it cannot be used as a joint sealant on this type of surface. Sumogrip white can therefore only be used on the bottom of natural stone tiles.
- When applying, make sure not to spill any sealant on the surface of materials.

Environmental Clauses:*Leed regulation:*

Sumogrip white conforms to the requirements of LEED. Low – Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOCcontent.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. DIPT Group reserves the right to modify products without prior notice.