

THE FOLLOWING SALT SPRAY TEST REPORT APPLIES TO ALL TIMco WINDOW SCREWS
MANUFACTURED FROM A2/302 AUSTENITIC STAINLESS STEEL.

ROTECH
LABORATORIES

MOXLEY INDUSTRIAL CENTRE
WESTERN WAY
WEDNESBURY
WEST MIDLANDS
WS10 7BG
TEL: 0121 505 4050
FAX: 0121 505 1115
www.rotechlabs.co.uk
info@rotechlabs.co.uk



0366

**Test
Report**

Our Ref: GBW Number 162554-4 Issue 1 Date 19/12/2016 Page 1 of 2

A/C No: M114

Tested For:-

T I MIDWOOD & COMPANY LIMITED
Green Lane
Wardle
Nantwich
Cheshire
CW5 6BJ

SALT SPRAY TESTING OF TIMCO 4.3 x 25mm WINDOW SCREW SAMPLES

INTRODUCTION

The finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

RELEVANT INFORMATION

Description: 20 off. Timco 4.3 x 25mm PVC Window Screw CSK-S/S Samples
Finish: Austenitic Stainless Steel
TIMco Code: 204 SS
Batch No. 5055017529759
Specification: Salt Spray Test in accordance with BS EN ISO 9227:2012
Test Duration: 504 Hours Salt Spray Exposure
Submitted By: Cris Tonks
Customer's Order No: 5277CT
Sample Receipt Date: 24/11/2016

RESULTS

Salt Spray Test (BS EN ISO 9227:2012)

The samples were exposed to a neutral 5% Salt Spray, for a test period of 504 hours.

Examination after every 24 hours revealed the following observations:-

24 – 504 Hours

The samples showed no evidence of red ferrous corrosion.

REPORT
COMPILED BY



G B Withers

Corrosion Science Technician

REPORT
APPROVED BY



G B Withers

Corrosion Science Technician

TESTS MARKED 'NOT UKAS ACCREDITED' IN THIS REPORT/CERTIFICATE ARE NOT INCLUDED IN THE UKAS ACCREDITATION SCHEDULE FOR OUR LABORATORY.
TESTS MARKED 'SC' HAVE BEEN SUBCONTRACTED.
RESULTS IN THIS REPORT RELATE ONLY TO THE ITEMS TESTED
OPINIONS AND INTERPRETATIONS EXPRESSED HEREIN ARE OUTSIDE THE SCOPE OF UKAS ACCREDITATION.
THIS TEST REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT WRITTEN APPROVAL OF THE LABORATORY